

**MULTI-SURFACE  
CERAMIC  
CLEARCOAT**  
PURE AIR COATING

**You will need:**

Pressure washer (Hot water preferred)  
Fan tip on wand  
Chemical tank or pump-up sprayer  
Soft bristle broom (blue)  
**SIMIX Multi-Surface Cleaner/Degreaser/Sanitizer**  
**SIMIX Multi-Surface Ceramic Clearcoat**  
Distilled or RO water

## Clean & Coat Pavers, Pool Decks and All Other Exterior Concrete

### INSTRUCTIONS

**AVOID CONTACT WITH GLASS.** Mask off windows where overspray or wind could effect. **SIMIX** Multi-Surface Ceramic Clearcoat will bond to unprotected glass immediately and will cause an uneven appearance

#### Clean with SIMIX Multi-Surface Cleaner/Degreaser/Sanitizer

**Step 1:** Dissolve **SIMIX Multi-Surface Cleaner/Degreaser/Sanitizer** in water. Use 1/2 large scoop per gallon of water for moderately soiled surfaces. Use 1 large scoop per gallon of water for extremely soiled surfaces.

**Step 2:** SPRAY. Spray on surface. Use HVLP unit or equivalent. (use a designated clean tank with no chemical contamination)

**Step 3:** SOAK. Let solution soak in for at least 20 minutes.

**Step 4:** WASH OFF. Pressure wash surface to rinse.

**Step 5:** LET DRY. Let surface visibly dry before coating.

#### Coat Surface

**Prepare SIMIX Multi-Surface Ceramic Clearcoat. Refer to Mixing/Dilution chart.**

**Check temperature and consult mixing chart for proper amounts.**

**Step 1:** APPLY. Apply with Graco or equivalent airless sprayer. Be careful not to overapply, product should not puddle

**Step 2:** BROOM. We recommend that you spray, then broom coating into pavers or concrete.

**Step 3:** LET DRY. Drying times will vary from 5 to 30 minutes. At 75°F and 65% relative humidity, the coating will dry in approximately 15–30 minutes. When visibly dry apply next coat. Apply at least 3 more coats.

Exterior surfaces	Concrete, Pavers, Pool Decks (minimum 4 coats)		
Surface Temperature	45° - 99°F	100° - 120°F (40% humidity)	100° - 120°F (less than 35% humidity)
SIMIX	1 Part	1 Part	1 Part
Distilled or RO water	6 Parts	9 Parts	14 Parts
Coverage/per mixed gal.	600 -1200 sq. ft.	500 -1000 sq. ft.	400 - 800 sq. ft.

Coverage rates will vary based on type of surface, porosity, ambient temperature, surface temperature and humidity.

#### MIXING INSTRUCTIONS

For best results and longevity of coating, mix SIMIX with distilled or RO water. Mix in a pump-up or backpack sprayer. Always add water first and SIMIX second.

**BEFORE MIXING, SHAKE GALLON OF SIMIX THOROUGHLY.**

**CONSULT MIXING CHART BELOW.** Pour proper amount of distilled or RO water first into sprayer. Then add proper amount of SIMIX concentrate and mix thoroughly.

**CHECK SURFACE TEMPERATURE.** Apply when surface is above 45°F and below 120°F. If the surface is over 120°F, pre-wet surface. Coverage rates will vary based on type of surface, porosity, ambient temperature, surface temperature and humidity.

**SIMIX**®